

## Technical Data Sheet

S10 - Hose-Silicone ø 10 Silver/Grey SS Braided S13 - Hose-Silicone ø 13 Silver/Grey SS Braided S19 - Hose-Silicone ø 19 Silver/Grey SS Braided

For water. Good behavior in contact with most chemicals. Temperature:  $-30^{\circ}$  C a  $+170^{\circ}$  C

## **RUBBER SPECIFICATION:**

CHEMICAL COMPOSITION: DENSITY: HARDNESS: TENSILE STRENGHT: ELONGATION: COLD RESISTANCE: HEAT RESISTANCE:

1.18 g / cm3 78 ° SHORE A ± 5 8 MPa 230 % HIGHER THAN -30 °C HIGHER THAN +170°C SILICONE ACCORDING TO ISO R1183 ACCORDING TO ASTM D2240 ACCORDING TO ISO R37 ACCORDING TO ISO R37

## CHARACTERISTIC OF THE STAINLESS STEEL BRAID:

WIRE: TENSILE STRENGHT: ELONGATION: STAINLESS STEEL AISI-304 DIAMETER 0.20 mm. 650-850 MPa ≥ 20 %

Change log

Date of change	Change	Version
May 23, 2019	Michael Arnesen   Mouldpro	001